

# TECHNICAL DATA SHEET



## 400N-S

Tube Filling Compound

Thixotropic water blocking compound suitable for filling at high line speeds into cable designs where a low viscosity is desired. Unigel 400N-S has a working temperature range from -50 to +80 °C and exhibits excellent resistance to oxidation for long term stability.

Properties	Typical Value	Test Method
Appearance	Translucent	Visual
Density, 25°C (g/ml)	0.86	ASTM D1475
Flash Point (°C)	≥220	ASTM D92
Drop Point (°C)	≥170	ASTM D566
Cone Penetration, 25°C (dmm)	≥430	ASTM D217 (M)
Cone Penetration, -40°C (dmm)	≥230	ASTM D217 (M)
Viscosity, 50 s <sup>-1</sup> , 25°C (Pa.s)	3.4	UNIGEL - CR Ramp 0-100 s <sup>-1</sup>
Oil Separation, 100°C, 24 hours (Wt %)	Zero	FTM 791-321 (M)
Volatile Loss, 100°C, 24 hours (Wt %)	≤1.0	FTM 791-321 (M)
Oxidation OIT, 190°C (min)	≥30	ASTM D3895
Acid Value (mg KOH/g)	≤0.1	ASTM D974-85
Water Content (ppm)	≤100	ASTM D4019-88
Hydrogen Generation, 80°C, 24 hours (µl/g)	≤0.02	UNIGEL
Fungal Growth	Nil	ASTM G21

Packaging Type	Net Weight (kg)	Supply Options
210 Litre Drum (liners available)	175kg	Single Journey
1000 Litre IBC	825kg	Single Journey
1000 Litre Unibag	750kg	Single Journey

### Compatibility

UNIGEL 400N-S is compatible with most cable grade polymers. Tests on typical acrylate coated optical fiber shows no reaction but it is recommended that compatibility tests are made with all materials likely to come into contact with 400N-S.

### Processing

UNIGEL 400N-S has been designed for pumping from ambient conditions for high speed loose tubing lines

The data presented herein is given in good faith and correct to the best of our knowledge at publication. Values quoted are typical and do not constitute a guarantee of performance and UNIGEL reserve the right to make alterations without notice. UNIGEL is a registered trademark of UNIGEL IP Ltd.

UNIGEL (UK) Ltd.  
Unit 7, Park View, Alder Close  
Eastbourne, East Sussex  
BN23 6QE,  
United Kingdom

UNIGEL (USA) Inc.  
1027 19<sup>th</sup> Street S.W  
Hickory, NC 28602  
United States of America

UG Technologies Sdn. Bhd.  
Lot 21, Block A,  
Lorong Keluli 1C, Seksyen 7  
40000 Shah Alam,  
Selangor, Malaysia